

CP-GK9-351C00

JET-KOTE™ DIGITAL INKJET PRINT RECEPTIVE PAPER AND FILM PRODUCTS TECHNICAL DATA SHEET

PRODUCT NUMBER

CP-GK9-351C00

PRODUCT NAME

Jet-Kote Satin/Perm/40#sck

TYPE

Satin IJ Paper

DESCRIPTION

A satin white paper designed to be compatible with most aqueous pigment and dye-based IJ inks, combined with a permanent hot melt adhesive and a 40#sck liner.

PRINT COMPATIBILITY

Aqueous pigment/dye inkjet and thermal transfer

FACESTOCK

3.5 mil white satin inkjet receptive paper

		<u>Value</u>	<u>Units</u>	ASTM Method
Caliper:		90.4	μm	
Basis Weight:		90	gsm	
Opacity:		93	percent	
Tensile:	MD	8.5	kg/15mm	
	CD	4.5	kg/15mm	
Tear:	MD	700	mN	

ADHESIVE

Permanent

ValueUnitsASTM MethodLoop Tack:5.59lbs/in²PSTC-16(Glass)

Peel Adhesion

20 Minute: 6.1/PT lbs/in PSTC-101(Glass)
Shear Adhesion: Medium PSTC-107(SS)

Minimum Application Temperature: 35°F Service Temperature Range: 0°F to +140°F

LINER

40# SCK

		<u>Value</u>	<u>Units</u>	ASTM Method
Caliper:		2.5	mil	
Basis Weight:		40	lbs/ream	
Tensile:	MD	40	lbf/in	D882
	CD	18	lbf/in	D882
Tear:	MD	30	percent	D882
	CD	35	percent	D882
Opacity:		89	percent	
Moisture:		4.5	percent	

SHELF LIFE

One year under standard storage and humidity conditions. For maximum product longevity, store out of direct sunlight and away from any fumes.

PRODUCT DISCLAIMER

Due to the variety and evolving technologies of OEMs, print engines, press capabilities and inks, all material constructions are sold with the understanding that the purchaser has independently tested and determined the suitability of each product for the application for which it is purchased. The seller disclaims any implied warranty of fitness of a product for a particular purpose. All materials should be tested thoroughly by the purchaser under end-use conditions to ensure they meet the requirements of a specific application.

Made In The USA under an ISO 9001 Quality Management System

© 2021 GENERAL DATA COMPANY, INC. ALL RIGHTS RESERVED