

Material Specification Sheet**Product:**

M-826

Description:

A white biaxially oriented top coated polypropylene film facestock with a cold temp hot melt adhesive and a bleached calendered liner.

Recommended Applications:

This material is recommended for a variety of applications. Particularly good for packaging material.

Facestock:

A white biaxially oriented top coated polypropylene film facestock with multiple layers.

		<u>Value</u>	<u>Units</u>
Basis Weight		32.2	lbs/3300 ft ²
Caliper:		2.6	mil
Tensile:	MD	13,053	lbs/in ²
	CD	29,008	lbs/in ²
Opacity:		90	%

Adhesive:

A cold temp hot melt adhesive that performs well on greasy and wet applications.

		<u>Value</u>	<u>Units</u>
Minimum Application temp:		10	°F
Service temp:		-50 to +145	°F
Shear:		157	minutes
90° Peel:			
	Stainless Steel	38	lb/in
Loop Tack:		72	lb/in

Liner:

A bleached calendered liner.

		<u>Value</u>	<u>Units</u>
Basis Weight:		41	lbs/3000 ft ²
Caliper:		2.5	mil
Tensile:	MD	34	lbs/in
	CD	21	lbs/in
Tear:	MD	34	grams
	CD	36	grams
Opacity:		69	%

Shelf Life:

One year, under standard storage and humidity conditions

PRODUCT DISCLAIMER

All labels and label material constructions are sold with the understanding that the purchaser has independently determined the suitability of each product for the application for which it is purchased. The seller disclaims any implied warranty of fitness of a product for a particular purpose. All materials should be tested thoroughly by the purchaser under end-user conditions to ensure they meet the requirements of a specific application.

